

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 85304734.8

(61) Int. Cl.⁴: C 08 G 63/06

(22) Date of filing: 03.07.85

A 61 L 17/00, C 08 G 63/10

(30) Priority: 06.07.84 JP 140356/84

(43) Date of publication of application:
26.02.86 Bulletin 86/9

(84) Designated Contracting States:
AT BE CH DE FR GB IT LI LU NL SE

(71) Applicant: WAKO PURE CHEMICAL INDUSTRIES, LTD.
10, Doshomachi 3-chome
Higashi-ku Osaka(JP)

(71) Applicant: Takeda Chemical Industries, Ltd.
27, Doshomachi 2-chome Higashi-ku
Osaka-shi Osaka, 541(JP)

(72) Inventor: Tanaka, Motoaki
13-3, Beascho 2-chome
Urawa Saitama 336(JP)

(72) Inventor: Ogawa, Yasuaki
32-503, 7 Nakahozumi 1-chome
Ibareki Osaka 567(JP)

(72) Inventor: Miyagawa, Tsutomu
2090-21, Kasahara
Kawagoe Saitama 350(JP)

(72) Inventor: Watanabe, Toshio
12-10, Kasumigaseki Higashi 2-chome
Kawagoe Saitama 350(JP)

(74) Representative: Lewin, John Harvey et al,
Elkington and Fife High Holborn House 52/54 High
Holborn
London WC1V 6SH(GB)

(64) Polymer and its production.

(67) A polymer or copolymer of lactic acid and/or glycolic acid which has a weight-average molecular weight of not less than about 5,000 and a dispersity of about 1.5 to 2 is advantageously used as a biodegradable polymer or copolymer for medical preparation.

EP 0 172 636 A1

- 1 -

POLYMER AND ITS PRODUCTION

The present invention relates to a polymer of lactic acid or glycolic acid, a copolymer of lactic acid and glycolic acid and a method for producing the polymer or the copolymer by a polycondensation reaction in the presence of a solid inorganic acid catalyst.

In recent years, degradable polymers have attracted a good deal of attention, for example, as a readily degradable polymer serving to mitigate environmental pollution by plastics and also as a biodegradable polymer for medical use.

As the method for producing a copolymer of lactic acid and glycolic acid, there is mentioned a method disclosed in U. S. Patent No. 4,273,920. In the U. S. Patent, it is stated that the copolymer being substantially free of polymerization catalyst is obtained by reacting lactic acid with glycolic acid in the presence of a readily removable strong acid ion-exchange resin, and removing the resin therefrom.

However, the copolymers produced by the above-described method all exhibit a dispersity in molecular weight as high as nearly 3 or more, and on the occasion of use, to give great complexity in factors involved in solubility and other aspects, thus being encountered with major problems in controlling such factors. Therefore, they cannot be said to be very favorable, when they are

used, for example, as a biodegradable polymer for medical use. In addition, this method allows the strong acid ion exchange resin being used as a polymerization catalyst to deteriorate due to heat during a polycondensation reaction under heating and to get dissolved in the resulting copolymer, thereby contributing to the development of coloration of the copolymer. Once the copolymer gets colored, furthermore, it is difficult to eliminate such coloration, and it is practically impossible to remove completely such coloration, and its coloration shows that the catalyst, i.e. strong acid ion-exchange resin, cannot be completely removed. It goes without saying that such coloration not only diminishes the values as an article of commerce but also is in the undesirable state, because it is attributed to impurities.

In view of such circumstances, the present inventors conducted repeatedly intensive research, and found a method for producing a polymer of lactic acid or glycolic acid and a copolymer of lactic acid and glycolic acid, which are effective and free from the above-mentioned disadvantages. Based on this finding and a further research, the present inventors have completed the present invention.

The present invention is directed to:

- (1) A polymer or copolymer of lactic acid and/or glycolic acid, which has a weight-average molecular weight of not less than about 5,000 and a dispersity of about 1.5 to 2, and
- (2) In a method for producing a polymer or copolymer of lactic acid and/or glycolic acid by subjecting lactic acid and/or glycolic acid to a polycondensation reaction, an improvement comprises employing a solid inorganic acid catalyst as a polycondensation catalyst.

In the method of the present invention, lactic acid and/or glycolic acid are/is employed, as the starting

materials, in the form of crystals, powders or granules as such, or in the form of an aqueous solution. The concentration of the solution is arbitrarily selected, preferably as high as possible, and more preferably not lower than about 85 % (w/w).

As the lactic acid and/or glycolic acid units employed in the present invention as a starting material, low molecular polymer of lactic acid or glycolic acid or low molecular copolymer of lactic acid and glycolic acid may be employed in the present method.

As the low molecular polymer of lactic acid or glycolic acid, there are mentioned an oligomer (e.g. dimer, trimer, etc.) of lactic acid, an oligomer (e.g. dimer, trimer, etc.) of glycolic acid and so on.

As the low molecular polymer or copolymer as a starting material, there are mentioned one which is produced by subjecting lactic acid and/or glycolic acid to polycondensation reaction in the absence of a catalyst under for example about 100 to 150°C/350 to 30 mmHg for more than about 2 hours, normally about 2 to 10 hours, more preferably while increasing the temperature and the degree of reduced pressure stepwise from about 105°C/350 mmHg to 150°C/30 mmHg for about 5 to 6 hours, to thereby remove water. In this process, a low molecular polymer or copolymer of molecular weight of about 2000 to 4000 is obtained.

Furthermore, as the low molecular copolymers, there are mentioned, for example, ones which are obtainable by the manners described in Kogyo Kagaku Zasshi (Journal of the Chemical Society of Japan), vol. 68, pp. 983-986 (1965), i.e. lactic acid and glycolic acid are reacted in a normal atmospheric pressure and in the absence of a catalyst at 202°C for 6 hours, or U. S. Patent No. 2,362,511, i.e. lactic acid and glycolic acid are reacted at a temperature of 200°C holding the mixture at that temperature for a period of about 2 hours and subsequently

continuing the heating for another period of about $\frac{1}{2}$ hour under vacuum.

The ratio of lactic acid to glycolic acid in the copolymer, when the object compound is a copolymer of these compounds, is preferably about 50 to 95 weight % of lactic acid and about 50 to 5 weight % of glycolic acid, preferably about 60 to 95 weight % of lactic acid and about 40 to 5 weight % of glycolic acid, more preferably about 60 to 85 weight % of lactic acid and about 40 to 15 weight % of glycolic acid. The ratio is more preferably about 75 ± 2 mol % of lactic acid and about 25 ± 2 mol % of glycolic acid.

In the present method, a solvent may be employed, when the starting materials are crystals, powders or granules, to dissolve these compounds. As the solvents, there are mentioned, for example, water, methanol, ethanol, acetone, etc.

A solid inorganic acid catalyst, which is usable in the present invention, includes, for example, acid clay, activated clay, bentonite, kaolin, talc, aluminum silicate, magnesium silicate, alumina bolia, silicic acid, etc. These can all be used, either solely or as a mixture of not less than two kinds thereof, and each is employed as such or after being washed with, for example, hydrochloric acid of a concentration of 5 to 20 % to remove metal ions, if necessary.

The amount of a solid inorganic acid catalyst used in the present method is normally about 0.5 to 30 % w/w preferably about 1 to 20 % w/w, based on the total amount of lactic acid and glycolic acid. The catalyst can be used in one or several portions.

The catalyst may be added to the reaction system in the course of the reaction.

The present method is preferably carried out under heating and reduced pressure. The heating is carried out by heating reaction system at about 150 to 250°C, preferably about 150 to 200°C. The reduced pressure is normally about 30 to 1 mmHg, preferably about 10 to 1

mmHg. The reaction time of the present polycondensation reaction is normally about not less than 10 hours, preferably about 10 to 150 hours, more preferably about 10 to 100 hours.

5 Referring to the reaction steps and conditions in the present method when lactic acid and/or glycolic acid are/is employed as the starting materials, the following are preferably mentioned: A heating reaction under reduced pressure may be allowed to proceed at about 100 to
10 150°C/350 to 30 mmHg for not less than about 2 hours, normally about 2 to 10 hours, for example, for about 5 to 6 hours while increasing the temperature and the degree of reduced pressure stepwise to about 105°C/350 mmHg to 150°C/30 mmHg, to thereby remove water, followed by a dehydration
15 polycondensation reaction at about 150 to 200°C/10 to 1 mmHg for not less than about 10 hours, normally up to about 100 hours may be adequate.

When the low molecular polymer or copolymer is employed as the starting material, preferable reaction
20 conditions are as follows: A dehydration polycondensation reaction is carried out at about 150 to 200°C/10 to 1 mmHg for not less than about 10 hours, normally up to about 100 hours may be adequate).

After the termination of the reaction, the objective
25 polymer or copolymer can be readily obtained by removing the used solid inorganic acid catalyst. The solid acid catalyst of the present invention can be easily removed for example by filtration with suction using ordinary qualitative filter paper. Through mere
30 hot filtration of the reaction solution or filtration after dissolution of the polymer or copolymer in a suitable solvent such as methylene chloride, dichloroethane, chloroform, acetone, in an amount of about equal to about 10-times that of the polymer or copolymer,
35 whereupon no subsequent treatment is required to be

carried out in the former case where the reaction solution is filtered as such and the employed solvent is concentrated or distilled off in the latter case where the reaction solution is filtered after being dissolved in a solvent. If desired, separation may be performed in accordance with the conventional method, for example, by pouring the filtered reaction solution, either directly or in the form of a concentrated filtrate in the case of a solvent being used, into a large amount of a precipitant, and if further required, purification may be carried out by reprecipitation, etc.

According to the present invention, there can be formed the polymer or copolymer consisting of lactic acid and/or glycolic acid units having a weight-average molecular weight of not less than about 5,000, preferably about 5,000 to 30,000, and the polymer or copolymer has a dispersity of about 1.5 to 2. Furthermore, the polymer or copolymer is colorless to almost white.

As the polymer or copolymer of the present invention has a low degree of dispersity, the distribution of the molecular weight of the polymer or copolymer is not wide.

Furthermore, as the solid inorganic acid catalyst is insoluble in the polymer or copolymer and in a solvent, the catalyst is completely removed from the reaction product and the resulting polymer or copolymer is free of coloration due to the catalyst.

The polymer or copolymer obtained by the present method can be utilized mainly as a base for drug preparation. For example, they can be advantageously utilized by incorporating steroid hormones, peptide hormones or anti-tumor agents, etc. into them to process into an embedded type or microcapsule type of controlled release preparations or by preparing fine particles containing an

anti-tumor agent to process into a therapeutic agent for embolization.

The Experiment Examples and Examples are described below to illustrate the present invention in more detail.

5 Experiment Example 1

To 160 g (1.5 mole as lactic acid) of a 85 % aqueous solution of lactic acid was added 6.8 g of a solid acid catalyst, and heating under reduced pressure was carried out for 6 hours under the stepwise varying conditions of 100 to 150°C/350 to 30 mmHg under a stream of nitrogen gas to remove the resulting water. Subsequently, 6.8 g of the solid acid catalyst was added additionally, followed by a dehydration polycondensation reaction at 175°C/5 mmHg for 72 hours.

15 Shown in Table 1 is the relationship between reaction time and weight-average molecular weight attained and its dispersity in the production of lactic acid polymers.

Also shown in Table 1 for the purpose of comparison are the results obtained with Dowex 50 (a cross-linked polystyrene resin, Dow Chemical Co., U.S.A.), a strongly acidic ion-exchange resin being commercially available, which was used as a polymerization reaction.

25 The weight-average molecular weight and dispersity ($\text{dispersity} = \frac{\text{weight-average molecular weight}}{\text{number-average molecular weight}}$) in the present specification were measured by gel permeation chromatography utilizing the standard polystyrene with the known molecular weight.

30

35

Table 1:

Type of polymerization catalysts and molecular weight attained and its dispersity

5	<u>Catalyst:</u>				
		Acid clay	Aluminum silicate	Activated clay	Dowex 50W
	Added amount (1)	6.8 g	6.8 g	6.8 g	6.8 g
	Added amount (2)	6.8 g	6.8 g	6.8 g	6.8 g
	12 hours of reaction time	-	6,200 (1.71)	5,000 (1.63)	-
10	24 hours of reaction time	8,900 (1.88)	11,200 (1.66)	8,800 (1.61)	9,100 (2.43)
	36 hours of reaction time	16,600 (1.72)	15,600 (1.65)	12,700 (1.62)	11,400 (2.53)
	48 hours of reaction time	-	19,100 (1.65)	16,700 (1.50)	14,900 (2.80)
	60 hours of reaction time	26,500 (1.73)	22,500 (1.66)	19,900 (1.67)	17,800 (2.81)
15	72 hours of reaction time	29,300* (1.77)	25,800 (1.66)	23,700 (1.81)	20,200 (2.80)
	Appearance of the polymer **	Almost white	Almost white	Almost white	Dark brown (the color deepens with time)

Note: * ; Reaction time of nearly 65 hours.

20 ** ; Each of the polymers obtained after the
 respective reaction time was dissolved in
 methylene chloride of the volume four times
 that of the polymer, and the solution was
 filtered using Toyo Filter Paper No. 131 [Toyo
 25 Roshi Co., Ltd., Japan] to remove the catalyst,
 and then concentrated to distill off the
 solvent; the resulting polymers were examined
 in accordance with JIS K 8004-2 (namely, about
 3 g of the specimen is taken on a watch glass,
 30 which is placed on a sheet of white paper and
 examined.).

In the Table 1, the added amount (1) of catalyst
 and the added amount (2) of catalyst denote an initially
 added amount of catalyst and an amount of catalyst
 35 additionally added at the time of the polycondensation

reaction at 175°C/5 mmHg after removal of water,
respectively while the reaction time means that at
175°C/5 mmHg. In the table, the parenthesized value
beneath the molecular weight attained indicates a
dispersity.

As is clear from Table 1, the present invention can
permit readily the production of high molecular weight
polymer with a weight-average molecular weight of not
less than about 5,000 being almost free from
polymerization catalyst, whereby the resulting polymers
show that colored appearance is hardly observed and the
polymers have dispersity of not more than 2, with the
polymerization reaction rate being evidently promoted by
the addition of the catalyst.

Experiment Example 2

After 160 g (1.5 mole) of a 85 % aqueous solution
of lactic acid and 38 g (0.5 mole) of glycolic acid were
mixed, 8.7 g of a solid acid catalyst was added to the
mixture, and heating under reduced pressure was carried
out at 100 to 150°C/350 to 30 mmHg under a stream of
nitrogen gas for 6 hours to remove the distilled water.
Subsequently, 8.7 g of the solid acid catalyst was added
additionally, followed by a dehydration condensation
reaction at 175°C/6 to 5 mmHg for 72 hours.

Shown in Table 2 is the relationship between
reaction time and weight-average molecular weight
attained in the production of copolymers of lactic acid
and glycolic acid.

Also, shown in Table 2 for the purpose of
comparison are the results obtained with a strongly
acidic ion-exchange resin (Dowex 50W) which was used as
a polymerization catalyst.

Table 2:

Type of polymerization catalysts and molecular weights attained

5	Catalyst: Type	Acid clay	Aluminum silicate	Activated clay	Dowex 50W
	Added amount (1)	8.7 g	8.7 g	8.7 g	8.7 g
	Added amount (2)	8.7 g	8.7 g	8.7 g	8.7 g
	12 hours of reaction time	-	5,100 (1.72)	-	-
10	24 hours of reaction time	12,600 (1.72)	11,700 (1.72)	10,200 (1.69)	10,500 (2.47)
	36 hours of reaction time	18,600 (1.73)	17,800 (1.74)	16,100 (1.65)	14,400 (2.44)
	48 hours of reaction time	22,900 (1.65)	22,000 (1.64)	20,400 (1.64)	18,900 (2.46)
	60 hours of reaction time	25,400 (1.68)	25,800 (1.68)	22,800 (1.63)	22,200 (2.47)
15	72 hours of reaction time	27,900 (1.76)	28,600 (1.66)	26,000 (1.63)	25,300 (2.76)
	Appearance of the polymer*	Almost white	Almost white	Almost white	Dark brown (the color deepens with time)

Note: * ; Each of the polymers obtained after the

20 respective reaction time was dissolved in methylene chloride of the volume four times that of the polymer, and the solution was filtered using Toyo Filter Paper No. 131 to remove the catalyst, and then, concentrated to distill off the solvent; the resulting polymers
25 were examined in accordance with JIS K 8004-2 (namely, about 3 g of the specimen is taken on a watch glass, which is placed on a sheet of white paper and examined.).

30 In the Table 2, the added amount (1) of catalyst and the added amount (2) of catalyst denote an initially added amount of catalyst and an amount of catalyst additionally added at the time of the polycondensation reaction at 175°C/5 mmHg after removal of water, respectively, while the reaction time means that at
35 175°C/5 mmHg. In the Table 2, the parenthesized value

- 11 -

beneath the molecular weight attained indicates a dispersity.

As is clear from Table 2, the present invention can permit readily the production of high molecular weight lactic acid-glycolic acid copolymers with a weight-average molecular weight of not less than about 5,000 being almost free from polymerization catalyst, whereby the resulting copolymers show that colored appearance is hardly observed, and all has dispersity as small as not more than 2, with the polymerization reaction rate being evidently promoted by the addition of the catalyst.

Furthermore, analysis of nuclear magnetic resonance spectrometry on said resulting copolymer of the present invention in CDCl_3 solution indicates the following composition of lactic acid and glycolic acid.

Copolymer ratio of the present copolymer mol % (weight %)			
Reaction time \ Catalyst	Acid Clay	Aluminum silicate	Activated Clay
12 hours	- - -	75.5:24.5 (79.3:20.7)	- - -
24 hours	75 :25 (78.8:21.2)	75 :25 (78.8:21.2)	75.5:24.5 (79.3:20.7)
36 hours	75 :25 (78.8:21.2)	75 :25 (78.8:21.2)	75 :25 (78.8:21.2)
48 hours	75 :25 (78.8:21.2)	76 :24 (79.7:20.3)	75 :25 (78.8:21.2)
60 hours	75.5:24.5 (79.3:20.7)	75.5:24.5 (79.3:20.7)	76 :24 (79.7:20.3)
72 hours	75.5:24.5 (79.3:20.7)	75.5:24.5 (79.3:20.7)	75.5:24.5 (79.3:20.7)

Example 1

Placed in a four-necked flask equipped with a thermometer, condenser and inlet tube for nitrogen gas were 160 g of a 85 % aqueous solution of lactic acid and 13.6 g of acid clay, and heating under reduced pressure was carried out under a stream of nitrogen gas over the period of 6 hours, while increasing the internal temperature and the degree of internal reduced pressure stepwise from 105°C and 350 mmHg to 150°C and 30 mmHg, and then the resulting water was removed. Successively, heating was conducted under reduced pressure of 3 mmHg and at the internal temperature of 175°C for 50 hours. The reaction solution was cooled to room temperature, and 400 ml of methylene chloride was added to it, followed by stirring to a solution. Then, the acid clay was removed by filtration using Toyo Filter Paper No. 131, and the filtrate was concentrated to dryness to give 100 g of an almost colorless polymer, which has a weight-average molecular weight of 22,000 and a dispersity of 1.75.

In order to determine the remaining catalyst in the resulting copolymer, a specimen of the copolymer was weighed out onto a dish of platinum and subjected to a fusing treatment with sodium carbonate, and then aluminum and silicon were determined colorimetrically by

application of the aluminon method and molybdenum blue method, with the result that neither of the metals was detected, leading to the conclusion that there was no contamination of the catalyst observed.

5

Example 2

A reaction was carried out in the manner of Example 1, except that 27.2 g of aluminum silicate was used as a catalyst, and there was obtained 92 g of an almost colorless polymer, which has a weight-average molecular weight of 21,900 and a dispersity of 1.70. The similar results were obtained when kaolin and talc were used in place of aluminum silicate as a catalyst.

10
In order to determine the remaining catalysts in the resulting copolymers, detection of the remaining catalysts was carried out in the manner of Example 1, with the result that there was no contamination of catalysts observed.

15

Example 3

In the manner of Example 1, 160 g of a 85 % aqueous solution of lactic acid was used, but 6.8 g of activated clay was charged in place of acid clay, whereupon after removal of the resulting water, a heating reaction was conducted at the internal pressure of 5 mmHg and at the internal temperature of 185°C for 96 hours to give 90 g of an almost white polymer. The resulting polymer has a weight-average molecular weight of 29,600 and a dispersity of 1.85.

20

25

In order to determine the remaining catalyst in the resulting polymer, detection of the remaining catalyst was carried out in the manner of Example 1, with the result that there was no contamination of catalyst observed.

30

Example 4

A reaction was conducted in the manner of Example 1, except that 160 g of a 85 % aqueous solution of lactic

35

acid, 38 g of glycolic acid and 17.4 g of activated clay were used, and there was obtained 122 g of an almost white copolymer, which has a weight-average molecular weight of 20,100 and a dispersity of 1.70, and shows a copolymerization composition of lactic acid and glycolic acid of 76 mol % : 24 mol % (79.7 weight % : 20.3 weight %).

In order to determine the remaining catalyst in the resulting copolymer, detection of the remaining catalyst was carried out in the manner of Example 1, with the result that there was no contamination of catalyst observed.

Example 5

Charged were 191 g of a 85 % aqueous solution of lactic acid, 17.5 g of glycolic acid and 9 g of acid clay, and after removal of the distilled water, a heating reaction was carried out at the internal pressure of 3 mmHg and at the internal temperature of 170°C for 96 hours to give 130 g of an almost white copolymer. The resulting copolymer has a weight-average molecular weight of 28,100 and a dispersity of 1.73, and a copolymerization composition of lactic acid and glycolic acid of 89 mol % : 11 mol % (90.9 weight % : 9.1 weight %).

The similar results were obtained, when the similar reaction was carried out with aluminum silicate, bentonite and kaolin being used as a catalyst instead.

In order to determined the remaining catalysts in the resulting copolymers, detection of the remaining catalysts was conducted in the manner of Example 1, with the result that there was no contamination of catalysts observed.

Example 6

146 g of a 93 % aqueous solution of lactic acid and 38 g of glycolic acid was used, a heating reaction was

conducted at the temperature of 202°C for 6 hours, whereby a copolymer with a weight-average molecular weight of 2,700 and a composition of lactic acid and glycolic acid of 75 mol % : 25 mol % was obtained.

5 Weighed in the same polymerization apparatus as used in Example 1 were 100 g of this copolymer and 10 g of acid clay, and heating was carried out under reduced pressure of 5 mmHg at internal temperature of 180°C for 50 hours. The reaction solution was cooled to room temperature, and
10 500 ml of methylene chloride was added to it, followed by stirring to a solution. Then, the acid clay was removed by filtration using Toyo Filter Paper No. 131 and the filtrate was concentrated to dryness to give 82 g of an almost colorless polymer, which showed a weight-average
15 molecular weight of 23,700 and a dispersity of 1.73, and a copolymerization composition of lactic acid and glycolic acid of 75 mol % : 25 mol % (78.8 weight % : 21.2 weight %).

In order to determine the remaining catalyst in the resulting polymer, detection of the remaining catalyst
20 was carried out in the manner of Example 1, with the result that there was no contamination of catalyst observed.

Example 7

A reaction was conducted in the manner of Example
25 6, except that 97 g of lactic acid dimer (Lactic acid lactate) and 54 g of glycolic acid dimer (Glycologlycolic acid) and 7.5 g of acid clay were used, and there was obtained 98 g of an almost white copolymer, which has a weight-average molecular weight of 21,000 and a dis-
30 persity of 1.75, and a copolymerization composition of lactic acid and glycolic acid of 59.5 mol % : 40.5 mol % (64.6 weight % : 35.4 weight %).

In order to determine the remaining catalyst in the resulting copolymer, detection of the remaining catalyst
35 was carried out in the manner of Example 1, with the result that there was no contamination of catalyst observed.

What we claim is:

1. A polymer or copolymer of lactic acid and/or glycolic acid, which has a weight-average molecular weight of not less than about 5,000 and a dispersity of about 1.5 to 2.
2. A polymer or copolymer as claimed in Claim 1, wherein the weight-average molecular weight is about 5,000 to 30,000.
3. A polymer as claimed in Claim 1, wherein the polymer consists of lactic acid units.
4. A copolymer as claimed in Claim 1, wherein the copolymer consists of lactic acid and glycolic acid.
5. A copolymer as claimed in Claim 4, wherein copolymer ratio is about 50 to 95 weight % of lactic acid and about 50 to 5 weight % of glycolic acid units.
6. A copolymer as claimed in Claim 4, wherein copolymer ratio is about 60 to 95 weight % of lactic acid and about 40 to 5 weight % of glycolic acid.
7. A copolymer as claimed in Claim 4, wherein the copolymer ratio is about 60 to 85 weight % of lactic acid and about 40 to 15 weight % of glycolic acid.
8. A copolymer as claimed in Claim 4, wherein the copolymer ratio is about 75 \pm 2 mol % of lactic acid and about 25 \pm 2 mol % of glycolic acid.
9. In a method for producing a polymer or copolymer of lactic acid and/or glycolic acid by subjecting lactic acid and/or glycolic acid to a polycondensation reaction, an improvement comprises employing a solid inorganic acid catalyst as a polycondensation catalyst.

10. A method as claimed in Claim 9, wherein the weight-average molecular weight of the polymer or copolymer is about not less than 5,000 and a dispersity of it is about 1.5 to 2.

11. A method as claimed in Claim 9, wherein a solid inorganic acid catalyst is one selected from the group consisting of acid clay, activated clay, bentonite, kaolin, talc, aluminium silicate, magnesium silicate, alumina bolia and silicic acid.

12. A method as claimed in Claim 9, wherein a solid inorganic acid catalyst is one selected from the group consisting of acid clay, activated clay and aluminium silicate.

Claims for contracting state: AT (Austria)

What we claim is:

1. In a method for producing a polymer or copolymer of lactic acid and/or glycolic acid by subjecting lactic acid and/or glycolic acid to a polycondensation reaction, an improvement comprises employing a solid inorganic acid catalyst as a polycondensation catalyst.
2. A method as claimed in Claim 1, wherein the weight-average molecular weight of the polymer or copolymer is about not less than 5,000 and a dispersity of it is about 1.5 to 2.
3. A method as claimed in Claim 1, wherein the polymer consists of lactic acid units.
4. A method as claimed in Claim 1, wherein the copolymer consists of lactic acid and glycolic acid.
5. A method as claimed in Claim 4, wherein the copolymer ratio is about 50 to 95 weight % of lactic acid and about 50 to 5 weight % of glycolic acid units.
6. A method as claimed in Claim 4, wherein the copolymer ratio is about 60 to 95 weight % of lactic acid and about 40 to 5 weight % of glycolic acid.
7. A method as claimed in Claim 4, wherein the copolymer ratio is about 60 to 85 weight % of lactic acid and about 40 to 15 weight % of glycolic acid.
8. A method as claimed in Claim 4, wherein the copolymer ratio is about 75±2 mol % of lactic acid and about 25±2 mol % of glycolic acid.
9. A method as claimed in Claim 1, wherein a solid inorganic acid catalyst is one selected from the group consisting of acid clay, activated clay, bentonite, kaolin, talc, aluminium silicate, magnesium silicate, alumina bolia and silicic acid.
10. A method as claimed in Claim 1, wherein a solid inorganic acid catalyst is one selected from the group consisting of acid clay, activated clay and aluminum silicate.



EP 85 30 4734

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
X	EP-A-0 058 481 (IMPERIAL CHEMICAL INDUSTRIES PLC) * page 22, lines 11-14; page 24, lines 6-21; claim 21 *	1-8	C 08 G 63/06 A 61 L 17/00 C 08 G 63/10
A	US-A-2 683 136 (N.A. HIGGINS) * claims 1,2; table 1; examples 1,2 *	1,4	
A	AT-B- 192 623 (J. KLEINE) * claim 1, page 2, lines 21-31; page 4, lines 36-39 *	1-4, 9, 10	
D,A	US-A-2 362 511 (W.O. TEETERS) * claim 1; page 1, column 2, lines 9-30 *	1,4-6	
D,A	US-A-4 273 920 (R.S. NEVIN) * claims 1-9 *	1,2,4-10	
A	US-A-3 498 957 (H.W. JACOBSON) * column 2, lines 1-55 *	1,9	
P,A	PATENT ABSTRACTS OF JAPAN, vol. 8, no. 212 (C-244)[1649], 27th September 1984; & JP - A - 59 96123 (SHOWA KOBUNSHI K.K.) 02-06-1984 (Cat. A)	1-3	
The present search report has been drawn up for all claims			
Place of search BERLIN		Date of completion of the search 01-10-1985	Examiner IDEZ C.G.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.